



Hybond®

PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

Product Number:

HY-80

Description:

Neoprene Contact Adhesive, Brush Grade

Typical Physical Properties:

Class: Extremely Flammable
Viscosity: 1000 cps
Dry Time: ~8 - 12 minutes
Solids: 19.0% +/- 1%
Open Time: 60 minutes
Color: Natural
Solvents: Organic Solvents

Flash Point: -4 deg F
Coverage: 152 sq ft/gal
Clean Up: Choice Brands 689 Cleaner
Coverage rate: 2.5 dry grams/sq ft minimum
VOC: 605 g/l (EPA method 24)
Shelf Life: 1 year from date of manufacture
Packaging: Totes, Drums and Pails

Qualifies for LEED®-NC & CI EQ Credit 4.4: *laminating adhesives shall contain no urea formaldehyde resins*

Properties:

- Premium flammable brush grade contact cement.
- Excellent adhesion to a variety of substrates including, but not limited to laminates, particle board, plywood, hardwood, leather, rubber and metal
- Excellent room temperature contactability
- Excellent green strength and high heat resistance
- Postformable
- Spreads easily and provides uniform coverage
- Fast drying formula
- One hour open time

Application:

1. For best results, agitate adhesive before use.
2. Substrates should be clean and free of moisture, dirt, oil and other contaminants.
3. For best results, adhesive and substrates should be allowed to acclimate to room temperature (approximately 60 °F or above) before adhesive application.
4. The adhesive can be applied with an animal hair or solvent-resistant brush, a short-nap roller, or a roll coater.
5. The adhesive should be applied at approximately 2.5 dry grams/square foot. The adhesive should cover 100% of the substrate surface. The substrate surface should exhibit a uniform glossy sheen when the adhesive is completely dry. Dull areas indicate insufficient coverage. Adhesive should be reapplied to these areas.
6. When bonding porous substrates, it is advisable to apply two coats of adhesive. The first coat will act as a sealer and prevent excessive absorption of adhesive into the substrate. After the



Hybond®

PRODUCT DATA SHEET

CHOICE BRANDS ADHESIVES, 666 REDNA TERRACE #500, CINCINNATI, OH 45215 513-772-1234

first coat has dried, apply a second coat. Allow the second adhesive coating to dry completely before assembly.

7. Allowing the contact adhesive to dry completely before assembly is essential to obtaining a secure, permanent bond. To check for adhesive dryness, press the back of your fingers onto the adhesive surface. If adhesive transfers to fingers, additional dry time is necessary. If there is no adhesive transfer, the substrates are ready for bonding.

8. If areas exist with excessive adhesive deposition, twist the fingers while pressing them onto the adhesive layer. This will break any skin that may have formed as the adhesive dries from the top surface down. If a skin has formed, allow additional dry time to ensure complete evaporation of the solvent before bonding.

9. Dry times can be improved through the use of air movement, drying ovens, lamps, etc.

10. Substrates may be indexed together and bonded once the adhesive is dry. Bonds must be made within the open time of the adhesive. (Open times vary by adhesive. See specification on Page 1.)

11. Uniform pressure on the bonded laminates is necessary to create strong, lasting bonds. 40 pounds per linear inch is recommended to ensure complete fusion between the two layers of adhesive. A pinch roller is the ideal method for applying uniform pressure. When used properly, a J-roller can also provide sufficient pressure for bonding.

12. All contact adhesive bonds are immediately able to be routed, trimmed, cut, filed and machined

Application Precautions:

Do not use in applications with copper components.

Do not use on polystyrene foams or plasticized vinyls

Do not mix with other adhesives. Thinning the adhesive is not recommended.

Storage Conditions:

Rotate stock, use oldest first.

Keep covered to prevent solvent loss and contamination.

Do not freeze. Do not store at high temperatures.

Do not store in direct sunlight.

Please Refer To The Material Safety Data Sheet For Further Information.